

	AP-5 PG 64-22	1621		2023-01-26 13:45
	520D120	RT2316214385		2023-01-18 13:00

, @15 kg/m ³	KSM 2002	1000	1041	
(15) cm	KSM 2254	100	140+	
,COC	KSM 2010	260	344	
FOAM ON HEAT,180	KSM 2201	NONE	NONE	
Loss on Heating wt%	KSM 2258	0.6	0.0	
가 ((%)) %	KSM 2252	55	63	
%	KSM 2252	110	106	
(25)	KSM 2252	60 ~ 80	72	
가 mass%	KSM 2202-2	99.0	99.9	
	KSM 2250	44.0 ~ 52.0	47.5	
@120 mm ² /s	ASTM D4402	To be reported	951.0	
@135 mm ² /s	ASTM D4402		427.7	
@150 mm ² /s	ASTM D4402	To be reported	216.0	
@180 mm ² /s	ASTM D4402	To be reported	72.2	
PG- (7)	KSF 2389	64	64	
PG-	KSF 2389	-22	-22	

K. W. Hwang

