

	AP-5 PG 64-22		1621		2024-01-16 08:48
	520D120		RT2416214547		2024-01-10 14:00

, @15 kg/m ³	KSM 2002	1000		1042	
(15) cm	KSM 2254	100		140+	
,COC	KSM 2010	260		342	
FOAM ON HEAT,180	KSM 2201	NONE		NONE	
Loss on Heating wt%	KSM 2258	0.6		0.0	
가 ((%)) %	KSM 2252	55		66	
%	KSM 2252	110		106	
(25)	KSM 2252	50 ~ 80		68	
가 mass%	KSM 2202-2	99.0		99.9	
	KSM 2250	44.0 ~ 52.0		47.5	
@120 mm ² /s	ASTM D4402	To be reported		1039.1	
@135 mm ² /s	ASTM D4402			463.8	
@150 mm ² /s	ASTM D4402	To be reported		232.7	
@180 mm ² /s	ASTM D4402	To be reported		76.9	
PG- (7)	KSF 2389	64		64	
PG-	KSF 2389	-22		-22	

K. W. Hwang

