

	AP-5 PG 64-22		1621		2024-03-04 08:46
	620D503		RT2416214569		2024-02-27 17:00

, @15 kg/m ²	KSM 2002	1000	1040	
(15) cm	KSM 2254	100	140+	
,COC	KSM 2010	260	348	
FOAM ON HEAT,180	KSM 2201	NONE	NONE	
Loss on Heating wt%	KSM 2258	0.6	0.0	
가 ((%)) %	KSM 2252	55	65	
%	KSM 2252	110	109	
(25)	KSM 2252	50 ~ 80	69	
가 mass%	KSM 2202-2	99.0	99.9	
	KSM 2250	44.0 ~ 52.0	48.0	
@120 mm ² /s	ASTM D4402	To be reported	959.3	
@135 mm ² /s	ASTM D4402		433.7	
@150 mm ² /s	ASTM D4402	To be reported	219.9	
@180 mm ² /s	ASTM D4402	To be reported	73.8	
PG- (7)	KSF 2389	64	64	
PG-	KSF 2389	-22	-22	

K. W. Hwang
