

	AP-5 PG 64-22	1621		2026-01-05 15:21
	520D121	RT2516214753		2025-12-19 21:00

, @15 kg/m ³	KSM 2002	1000	1040	
(15) cm	KSM 2254	100	140+	
, COC	KSM 2010	260	356	
FOAM ON HEAT, 180	KSM 2201	NONE	NONE	
Loss on Heating wt%	KSM 2258	0.6	0.0	
가 ((%)) %	KSM 2252	55	64	
%	KSM 2252	110	100	
(25)	KSM 2252	50 ~ 80	64	
가 mass%	KSM 2201	99.0	99.9	
	KSM 2250	44.0 ~ 52.0	47.5	
@120 mm/s	ASTM D4402	To be reported	1001.2	
@135 mm/s	ASTM D4402		449.4	
@150 mm/s	ASTM D4402	To be reported	226.6	
@180 mm/s	ASTM D4402	To be reported	75.4	
PG- (7)	KSF 2389	64	64	
PG-	KSF 2389	-22	-22	

최명수

