

	AP-5 PG 64-22		1621		2025-04-04 13:19
	520D120		RT2516214671		2025-02-25 01:00

, @15 kg/m ³	KSM 2002	1000	1041	
(15) cm	KSM 2254	100	140+	
,COC	KSM 2010	260	350	
FOAM ON HEAT,180	KSM 2201	NONE	NONE	
Loss on Heating wt%	KSM 2258	0.6	0.0	
가 ((%)) %	KSM 2252	55	66	
%	KSM 2252	110	103	
(25)	KSM 2252	50 ~ 80	71	
가 mass%	KSM 2202-2	99.0	99.9	
	KSM 2250	44.0 ~ 52.0	47.5	
@120 mm ² /s	ASTM D4402	To be reported	957.7	
@135 mm ² /s	ASTM D4402		426.2	
@150 mm ² /s	ASTM D4402	To be reported	213.6	
@180 mm ² /s	ASTM D4402	To be reported	70.7	
PG- (7)	KSF 2389	64	64	
PG-	KSF 2389	-22	-22	

최명수

