

	AP-5 PG 64-22		1621		2024-07-01 10:08
	620D503		RT2416214609		2024-06-23 09:00

, @15 kg/m ³	KSM 2002	1000	1041		
(15) cm	KSM 2254	100	140+		
,COC	KSM 2010	260	352		
FOAM ON HEAT,180	KSM 2201	NONE	NONE		
Loss on Heating wt%	KSM 2258	0.6	0.0		
가 ((%)) %	KSM 2252	55	70		
%	KSM 2252	110	110		
(25)	KSM 2252	50 ~ 80	66		
가 mass%	KSM 2202-2	99.0	99.9		
	KSM 2250	44.0 ~ 52.0	47.5		
@120 mm ² /s	ASTM D4402	To be reported	991.6		
@135 mm ² /s	ASTM D4402		444.5		
@150 mm ² /s	ASTM D4402	To be reported	223.8		
@180 mm ² /s	ASTM D4402	To be reported	74.4		
PG- (7)	KSF 2389	64	64		
PG-	KSF 2389	-22	-22		

K. W. Hwang

